



LAMIERE



LAMIERE PIANE NERE LUCIDE DECAPATE E ZINCATE

Spessore mm	Peso Kg/m ²	Formato		
		1000x2000	1250x2500	1500x3000
0,4	3,140	6,28	9,81	14,13
0,5	3,925	7,85	12,27	17,66
0,6	4,71	9,42	14,72	21,20
0,8	6,28	12,56	19,63	28,26
1	7,85	15,70	24,53	35,33
1,2	9,42	18,84	29,44	42,39
1,5	11,77	23,55	36,80	52,99
2	15,70	31,40	49,06	70,65
2,5	19,62	39,25	61,33	88,31
3	23,55	47,10	73,59	105,98
4	31,40	62,80	98,13	141,30
5	39,25	78,50	122,66	176,63
6	47,10	94,20	147,19	211,95
7	54,95	109,90	171,72	247,28
8	62,80	125,60	196,25	282,60
10	78,50	157,00	245,31	353,25
12	94,20	188,40	294,28	423,90
15	117,75	235,50	367,97	529,88
20	157,00	314,00	490,63	706,50

LAMIERE DECAPATE DD11-S235

LAMIERE NERE S235-S355

LAMIERE CORTEN S 355

Spessore mm	Peso Kg/m ²	Formato		
		1000x2000	1250x2500	1500x3000
3	23,55	47,10	73,59	105,98
4	31,40	62,80	98,13	141,30
5	39,25	78,50	122,66	176,63
6	47,10	94,20	147,19	211,95
7	54,95	109,90	171,72	247,28
8	62,80	125,60	196,25	282,60
10	78,50	157,00	245,31	353,25


LAMIERE STRIATE

Spessore mm	Peso Kg/m ²	Formato		
		1000x2000	1250x2500	1500x3000
2,5	22,2	44,4	69,4	99,9
3	28,6	57,2	89,4	127,7
4	36,5	73,0	114,1	164,3
5	44,3	88,6	138,4	199,4
6	52,1	104,2	162,8	234,5
8	67,8	135,6	211,9	305,1
10	83,6	167,2	261,2	376,2

LAMIERE BUGNATE

Spessore mm	Peso Kg/m ²	Formato		
		1000x2000	1250x2500	1500x3000
2	16,97	33,9	53,0	76,4
2,5	20,87	41,7	65,2	93,9
3	27,05	52,1	81,4	117,2
4	33,95	67,9	106,1	152,8
5	41,75	83,5	130,5	187,9
6	52,10	104,2	162,8	234,5
8	67,9	135,8	212,2	305,6





CARATTERISTICHE TECNICHE

Tipo di acciaio	ReH N/mm ² min.	Rm N/mm ² min.	A5 % min.	Piegabilità, Ri	
				2-6 mm	>6 mm
Domex 220 YP	220	320	30	0,3 x t	0,5 x t
Domex 240 YP	240	360	28	0,5 x t	0,7 x t
Domex 280 YP	280	350	28	0,8 x t	0,9 x t
Domex 310 YP	310	380	26	1,0 x t	1,1 x t
Domex 355 YP	355	420	24	1,0 x t	1,3 x t
Domex 390 YP	390	460	22	1,2 x t	1,5 x t
Domex 420 YP	420	480	21	1,2 x t	1,5 x t

Tipo di acciaio	ReH N/mm ² min.	Rm N/mm ² min.	A5 % min.	Piegabilità, Ri	
				2-6 mm	>6 mm
Domex 355 XP	355	420	24	0,5 x t	0,8 x t
Domex 390 XP	390	460	22	0,6 x t	1,0 x t
Domex 420 XP	420	480	21	0,6 x t	1,0 x t
Domex 490 XP	490	550	18	0,8 x t	1,4 x t
Domex 590 XP	590	650	15	1,5 x t	1,8 x t
Domex 640 XP	640	700	15	1,5 x t	1,8 x t
Domex 690 XP	690	750	15	1,6 x t	1,8 x t
Domex 740 XP	740	790	13	1,8 x t	2,0 x t

LAMIERE FORATE

Spessore	Diametro foro	Passo	Formato
1	2,00	3,5	1000 x 2000
1	5,00	8	1000 x 2000
1	8,00	12	1000 x 2000
1,2	5,00	8	1000 x 2000
1,2	8,00	12	1000 x 2000
1,5	6	9	1000 x 2000
1,5	8	12	1000 x 2000
1,5	10	15	1000 x 2000
2	8	12	1000 x 2000
2	10	15	1000 x 2000
2	12	18	1000 x 2000
2	20	28	1000 x 2000
3	8	12	1000 x 2000
2	asola 10 x 20	-	1000 x 2000

